

Crossover effects in the Wolf–Villain model of epitaxial growth in 1+1 and 2+1 dimensions

Pavel Šmilauer*

*Interdisciplinary Research Centre for Semiconductor Materials, Imperial College, London
SW7 2BZ, United Kingdom*

Miroslav Kotrla

*Institute of Physics, Czech Academy of Sciences, Na Slovance 2, 180 40 Praha 8, Czech Republic
(February 1, 2008)*

Abstract

A simple model of epitaxial growth proposed by Wolf and Villain is investigated using extensive computer simulations. We find an unexpectedly complex crossover behavior of the original model in both 1+1 and 2+1 dimensions. A crossover from the effective growth exponent $\beta_{\text{eff}} \approx 0.37$ to $\beta_{\text{eff}} \approx 0.33$ is observed in 1+1 dimensions, whereas additional crossovers, which we believe are to the scaling behavior of an Edwards–Wilkinson type, are observed in both 1+1 and 2+1 dimensions. Anomalous scaling due to power-law growth of the average step height is found in 1+1 D, and also at short time and length scales in 2+1 D. The roughness exponents ζ_{eff}^c obtained from the height–height correlation functions in 1+1 D ($\approx 3/4$) and 2+1 D ($\approx 2/3$) cannot be simultaneously explained by any of the continuum equations proposed so far to describe epitaxial growth.

68.55.-a, 68.35.Fx, 61.50.Cj, 64.60.Ht

Typeset using REVTeX

Simple (“toy”) models of surface growth have become very popular recently, mainly as examples of externally driven non-equilibrium systems that exhibit simple (yet nontrivial) scaling behavior.¹ The focus is on the surface width (roughness) w defined as $w = \langle \sqrt{\overline{h^2} - \bar{h}^2} \rangle$ (the overbars denote spatial averages, $\langle \rangle$ a statistical average), *i.e.*, the variance of the surface height profile $h(\mathbf{r}, t)$. The surface width scales with the time t and the linear dimension of the substrate L as $w(t, L) \propto L^\zeta f(t/L^z)$, where the scaling function $f(x)$ has the properties $f(x) = \text{const}$, $x \gg 1$ and $f(x) \propto x^\beta$, $x \ll 1$, $\beta = \zeta/z$. Thus, w grows according to a power law, $w \propto t^\beta$, until a steady state characterized by a constant value of the width is reached after a time t_{sat} proportional to L^z . The value of the saturated width w_{sat} varies with the system size according to $w_{sat} \propto L^\zeta$. The exponents ζ and β (or ζ and z) characterize the scaling behavior of the roughness for a particular model and determine its universality class in analogy with theory of critical phenomena.

Alternatively, one can study the surface roughness using the height–height correlation function $G(\mathbf{r}, t) = \langle [h(\mathbf{x} + \mathbf{r}, t) - h(\mathbf{x}, t)]^2 \rangle$ which obeys the scaling relation¹ $G(r, t) \propto r^{2\zeta^c} g(r/t^{1/z^c})$, where the scaling function $g(x)$ is constant for $x \ll 1$ and $g(x) \propto x^{-2\zeta^c}$ for $x \gg 1$ (equivalently, the structure factor S can be used, see e.g. Ref. 2). In most of growth models the exponents obtained using the two different methods are equal.¹

Scaling behavior of the surface roughness can be investigated using continuum, stochastic differential equations which in the case of conserving models with surface diffusion have the form

$$\frac{\partial h(\mathbf{r}, t)}{\partial t} = -\nabla \cdot \mathbf{j}(\mathbf{r}, t) + \eta(\mathbf{r}, t) \quad , \quad (1)$$

where $\eta(\mathbf{r}, t)$ is a zero mean, random noise term in the incoming flux, and the current $\mathbf{j}(\mathbf{r}, t)$ is a function of the derivatives of $h(\mathbf{r}, t)$. In a number of recent theoretical studies,^{3–11} models in which surface diffusion is the dominant physical mechanism of the surface smoothing were studied. The scaling relation $2\zeta = z - d'$ (where d' is the substrate dimension) holds for these models.⁴ The most often studied cases were $\mathbf{j} \propto -\nabla h$ [Edwards–Wilkinson (EW) model¹²], $\mathbf{j} \propto \nabla \nabla^2 h$ (the *linear* diffusion model^{3,13}), and $\mathbf{j} \propto \nabla(\nabla h)^2$ and $\mathbf{j} \propto (\nabla h)^3$ (the

nonlinear diffusion models^{4,6,11} which we will denote I and II, respectively). The predicted values of exponents are^{3,4,6} $\beta^{EW} = (3 - d)/4$, $\zeta^{EW} = (3 - d)/2$, $\beta^{lin} = (5 - d)/8$, $\zeta^{lin} = (5 - d)/2$, $\beta^{nonlin-I} = (5 - d)/(7 + d)$, $\zeta^{nonlin-I} = (5 - d)/3$, and $\beta^{nonlin-II} = (5 - d)/2(3 + d)$, $\zeta^{nonlin-II} = (5 - d)/4$ where $d = d' + 1$. It should be noted that these values are usually based on renormalization group (RG) calculations within the one-loop approximation (e.g., Refs. 6,14) or on Flory-type approximation (Ref. 3).

Alternative approach is to employ a powerful computer and study discrete models with microscopic rules reflecting physically important surface processes.¹⁵ From a wide variety of discrete models we focus our attention on the one proposed by Wolf and Villain⁴ (WV) which is based on the solid-on-solid model of crystal growth¹⁶ and has been designed with growth by molecular-beam epitaxy (MBE) in mind. The growth rules of the model (see below) are supposed to mimic surface diffusion, the principal mechanism of surface smoothing during MBE. Original simulations of the model⁴ in 1+1 D yielded exponents $\beta_{\text{eff}} = 0.365 \pm 0.015$ and $\zeta_{\text{eff}} = 1.4 \pm 0.1$ (thus $z_{\text{eff}} = 3.8 \pm 0.5$) in agreement with the theoretical prediction of the *linear* model. However, a subsequent numerical work⁷ has shown that in 2+1 D the values of the exponents are $\beta_{\text{eff}} = 0.206 \pm 0.02$ and $\zeta_{\text{eff}} = 0.66 \pm 0.03$ (thus $z_{\text{eff}} = 3.2 \pm 0.5$) which correspond to the prediction of the *nonlinear* model I. The puzzling difference between the behavior of the model in 1+1 and 2+1 D has been confirmed in another numerical study.⁸ The possible explanation could be a slow crossover from exponent of the linear model to the exponent of the nonlinear model I observable in 1+1 D only for large system sizes and long times, similar to a crossover observed in a full-diffusion solid-on-solid model.⁹ To complicate the situation even further, it has been proposed recently by Krug, Plischke, and Siegert¹⁰ that the WV model should cross over to EW behavior for more than $\approx 10^6$ (1+1 D) or $\approx 2 \times 10^4$ (2+1 D) deposited layers. This result was based on the study of the inclination-dependent diffusion current which is supposed to generate the EW term $(\nabla^2 h)$ in continuum differential equations.^{15,17} The EW term is more relevant (in the RG sense) than all allowed nonlinear terms¹⁴ and governs the asymptotical behavior of the model. The long time needed to observe the asymptotic regime may be explained as due to a very small coefficient in front

of the EW term. Finally, it has been found very recently that the WV model in 1+1 D does not fulfill standard scaling and that different values of the exponents are obtained from behavior of the surface width and the correlation function or the structure factor.¹¹ The exponents obtained in 1+1 D from the behavior of the structure factor were $\zeta_{\text{eff}}^c = 0.75 \pm 0.05$ and $z_{\text{eff}}^c = 2.4 \pm 0.1$ (thus $\beta_{\text{eff}}^c \approx 0.31$) very close to the nonlinear model II predictions.¹¹ The authors also suggested that this anomalous behavior is present in 2+1 D as well.

The need for better simulation data apparent from the above summary has motivated the present work. We performed large-scale simulations of the WV model in 1+1 and 2+1 D. In 1+1 D, we used system sizes as large as $L = 40\,000$ sites and deposited up to $2^{27} \approx 1.3 \times 10^8$ layers whereas in 2+1 D we used lattice sizes of up to 1000×1000 depositing up to $2^{17} \approx 1.3 \times 10^5$ layers. Our results for exponents obtained from the surface width show (i) a crossover from $\beta_{\text{eff}} \approx 0.37$ (β^{lin}) to $\beta_{\text{eff}} \approx 0.33$ ($\beta^{\text{nonlin-I}}$) in 1+1 D, (ii) crossovers from $\beta_{\text{eff}} \approx \beta^{\text{nonlin-I}}$ to the scaling behavior which we believe is of the EW model in both 1+1 and 2+1 D. Exponents calculated from the correlation function are in agreement with those of the nonlinear model II in 1+1 D ($\zeta_{\text{eff}}^c \approx 0.75$) and the nonlinear model I in 2+1 D ($\zeta_{\text{eff}}^c \approx 0.65$).

The microscopic rules of the basic model are the same as in Ref. 4. In every time step, a particle is added at a randomly chosen lattice site and then relaxes toward a nearest-neighbor site which offers the highest *coordination* (the number of nearest neighbors) where it sticks for the rest of the simulation. If the number of nearest neighbors cannot be increased, particularly in the case of *tie* (one or more neighboring sites have the same coordination as the original site) the particle stays at the initial position. The generalization to 2+1 D is straightforward.

In 1+1 D, we carried out simulations for lattice sizes $L=150, 300, 600, 800, 1000, 2000$, and $40\,000$ depositing from 2^{25} to 2^{27} layers (except for $L = 40\,000$ where only 2^{23} layers were deposited), see Fig. 1. (Note that the curves for lattice sizes $L \geq 800$ have been offset in Fig. 1 to avoid confusion due to overlapping data points; statistical errors of the data points are not larger than the symbols size.) The crossover of the exponent β_{eff} from the

value 0.372 ± 0.007 corresponding to the linear model ($\beta^{lin} = \frac{3}{8}$) to $\approx 0.336 \pm 0.009$ in very good agreement with the nonlinear model I prediction ($\beta^{nonlin-I} = \frac{1}{3}$) can be best observed for the largest simulated lattice, $L = 40\,000$. It is apparent from Fig. 1 that this crossover takes place after approximately $2^{15} \approx 3 \times 10^4$ layers have been deposited. The values of w_{sat} we have obtained (48 ± 1 , 91 ± 10 , and 209 ± 20 for $L = 150, 300$, and 600 , respectively), give $\zeta_{eff} = 1.05 \pm 0.1$, in very good agreement with the nonlinear model I prediction, $\zeta_{eff}^{nonlin-I} = 1$.

However, a more surprising observation can be made after close inspection of the data in Fig. 1. All the curves (with the possible exception of the one for $L = 40\,000$ where fewer layers were deposited) show another decrease in the value of the exponent β_{eff} after the deposition of $2^{21} \approx 2 \times 10^6$ layers. The curves for $L \geq 800$ seem to follow the slope corresponding to the value $\beta = \frac{1}{4}$ of the EW model in 1+1 D (see Fig. 1). Because the time $t_{sat}(L)$ needed for the saturation depends on the system size as L^z , we obtain $t_{sat}(L = 2000) > 2^{27}$ based on our results for t_{sat} for small lattice sizes (even if we use $z^{nonlin-II} = 5/2$). Moreover, the position of the crossover seems not to depend on the lattice size. Hence we can exclude that this is the effect of the saturation.

Similar behavior is revealed by an inspection of 2+1 D results in Fig. 2. The data given for the lattice sizes $L = 500$ and $L = 1000$, correspond at first (between $\approx 2^3$ and 2^{10} layers deposited) to the value of $\beta_{eff} = 0.22 \pm 0.05$, very close to (but definitely higher than) the nonlinear model I prediction $\frac{1}{5}$. After $\approx 10^4$ layers are deposited, a crossover takes place. Again it cannot be due to the vicinity of the saturation regime because the estimate of t_{sat} in 2+1 D for $L = 500$ is larger than 2^{22} layers based on our previous results⁷ and the position of the crossover does not shift with the lattice size. A logarithmic increase of the roughness ($\beta^{EW} = 0$) is expected for the EW model in 2+1 D. Double-logarithmic and semilogarithmic plots of the last seven data points (averaged over the both curves) are shown in the inset of Fig. 2. The statistics of the data are insufficient to draw a definitive conclusion, but it seems that the semilogarithmic plot follows a straight line whereas the log-log one is curved. Thus, we believe our data suggest that in both 1+1 and 2+1 D we observe crossovers to the scaling behavior of the EW model predicted by Krug *et al.*¹⁰ and it should be noted that

even the positions of these crossovers agree well with this prediction.

Following the paper by Schroeder *et al.*¹¹ we also studied the behavior of $G(r, t)$. The time dependence of $G(r, t)$ in 1+1 and 2+1 D is shown in Fig. 3. The exponent $\zeta_{\text{eff}}^c = 0.75 \pm 0.03$ we obtained in 1+1 D using the initial slope of the correlation function for $t = 2^{19}$ monolayers and $L = 40\,000$ (Fig. 3 (a)) differs substantially from the value $\zeta_{\text{eff}} \approx 1$ obtained from the surface width behavior at later times (see above) and corresponds to $\zeta^{\text{nonlin-II}} = 3/4$. However, the value $\zeta_{\text{eff}}^c = 0.65 \pm 0.03$ obtained in 2+1 D (Fig. 3 (b)) for $L = 500$ and $t = 2^{17}$ monolayers is definitely different from 2+1 D value of $\zeta^{\text{nonlin-II}} = 1/2$ and is much closer to $\zeta^{\text{nonlin-I}} = 2/3$ which was also obtained from the surface width behavior.⁷ The values of the exponents ζ_{eff}^c obtained from $G(r, t)$ are thus to the best of our knowledge inconsistent with any simple model of epitaxial growth proposed so far.

In agreement with Ref. 11, we see the initial power-law increase of the average step height $G(1, t) \propto t^\lambda$ with $\lambda = 0.38 \pm 0.01$ in 1+1 D, and $\lambda = 0.095 \pm 0.003$ in 2+1 D, see the insets in Fig. 3. In Ref. 11, it is shown how this can explain effective exponents corresponding to the linear equation and the discrepancy between ζ_{eff} and ζ_{eff}^c in 1+1 D provided the nonlinear model II is used. Notice also that the crossover from the exponent $\beta_{\text{eff}} \approx 0.375$ to the value $\beta_{\text{eff}} \approx 0.33$ coincides with the beginning of $G(1, t)$ saturation. In 2+1 D, if we use the values of the *nonlinear model I* and $\lambda \approx 0.095$, we obtain $\zeta_{\text{eff}} \approx 0.84$ and $\beta_{\text{eff}} \approx 0.23$. The value of β_{eff} is in agreement with the results obtained here for short times $t \leq 2^{10}$ [see above; notice again that this is the region where we observe the power-law growth of $G(1, t)$] and also the value of ζ_{eff} is not inconsistent with the initial slope of the plot w vs. L in Fig. 2 of Ref. 7. Hence, the theory of Ref. 11 agrees with our results provided we use different “underlying” models in 1+1 and 2+1 D. The anomalous behavior due to power-law growth of $G(1, t)$ is much weaker in 2+1 D but can be observed at short time and length scales.

We also tried to find changes in the correlation function behavior that should take place following the crossovers which we suppose are to the EW behavior (see the thick lines in Fig. 3). In 1+1 D [Fig. 3 (a)], a decrease to the value of $\zeta_{\text{eff}}^c \approx 2/3$ is observed for $L = 2000$ and 2^{27} monolayers deposited, but this is still significantly higher than the EW model value

$\zeta^{EW} = 1/2$. In 2+1 D [Fig. 3 (b)], the behavior of the correlation function after the crossover does not change appreciably. A probable explanation is that the range of length scales (larger than the relevant crossover length) where $G(r, t)$ is influenced by the EW behavior is too short to be resolved in our data. However, we have found that the structure factor calculated for $L=2000$ and 2^{27} monolayers does at large wavelengths follow the slope -2 expected for the EW behavior. Statistics of these data are not sufficient to provide unambiguous proof and more work is needed.

In conclusion, we have studied kinetic roughening in 1+1 and 2+1 dimensions of a simple model of epitaxial growth proposed by Wolf and Villain.⁴ From the study of the surface width in 1+1 D, we have found a crossover from the scaling behavior of a linear differential equation proposed to describe MBE growth ($\beta_{\text{eff}} \approx 0.37$) to that corresponding to a nonlinear model I equation ($\beta_{\text{eff}} \approx 0.33$). According to Ref. 11 and our results, unusual behavior of the model in 1+1 D is due to a power-law growth of the average step height, $G(1, t) \propto t^\lambda$ where $\lambda \approx 0.38$ in 1+1 D and ≈ 0.095 in 2+1 D. As a consequence, the exponent ζ_{eff}^c obtained in 1+1 D from the height-height correlation function differs from the value obtained from the scaling of the surface width and does not change during the crossover. Its value in 1+1 D ($\zeta_{\text{eff}}^c \approx 3/4$) corresponds to another nonlinear model II proposed by Lai and Das Sarma.⁶ However, the value of the exponent $\zeta_{\text{eff}}^c \approx 2/3$ in 2+1 D is consistent with the nonlinear model I. One possibility of how to explain the discrepancy between the behavior in 1+1 and 2+1 D in terms of a continuum equation is to suppose that both relevant nonlinearities $[\nabla^2(\nabla h)^2$ and $\nabla(\nabla h)^3]$ are present but with different coefficients (and thus different importance) in 1+1 and 2+1 D.

In both 1+1 and 2+1 D, we see additional crossovers and our results seem to indicate these are to the scaling behavior of the EW model. The conclusion that the asymptotic behavior of the “ideal” MBE growth model is of EW type is in agreement with the recent suggestion by Krug *et al.*¹⁰. It would be interesting to see this crossover also in other discrete models, in particular in the full-diffusion model of Ref. 9 which was very successful in describing the initial stages of MBE growth. In some variants of the models with surface

diffusion, the final crossover to the EW behavior may be absent and instead the instability may develop. We expect this kind of behavior in models with barriers to interlayer transport.

We thank Professor D. Wolf and Professor D.D. Vvedensky for stimulating discussions and communicating their results prior to publication, and to Dr. M. Wilby for a critical reading of the first version of the manuscript. The calculations reported here were performed on a Meiko Infinity Series i860 Computing Surface at Imperial College and on Cray Y/MP-EL at the Institute of Physics. Work performed at Imperial College was supported by Imperial College and the Research Development Corporation of Japan. The work was supported in part by grant No. 110110 of the Academy of Sciences of Czech Republic.

REFERENCES

- * Also at: Department of Physics, The Blackett Laboratory, Imperial College, London SW7 2BZ, United Kingdom; on leave from Institute of Physics, Cukrovarnická 10, 162 00 Praha 6, Czech Republic
- ¹ For reviews, see, e.g., F. Family, *Physica A* **168**, 561 (1990); J. Krug and H. Spohn, in *Solids Far from Equilibrium: Growth, Morphology and Defects*, edited by C. Godrèche, (Cambridge University Press, Cambridge, 1990), p. 479; M. Kotrla, *Czech. J. Phys. B* **42**, 449 (1992).
- ² M. Plischke, Z. Rácz, and D. Liu, *Phys. Rev. B* **35**, 3485 (1987).
- ³ J. Villain, *J. Phys. I* **1**, 19 (1991).
- ⁴ D.E. Wolf and J. Villain, *Europhys. Lett.* **13**, 389 (1990).
- ⁵ S. Das Sarma and P. Tamborenea, *Phys. Rev. Lett.* **66**, 325 (1991).
- ⁶ Z.-W. Lai, S. Das Sarma, *Phys. Rev. Lett.* **66**, 2348 (1991).
- ⁷ M. Kotrla, A.C. Levi and P. Šmilauer, *Europhys. Lett.* **20**, 25 (1992).
- ⁸ S. Das Sarma and S.V. Ghaisas, *Phys. Rev. Lett.* **69**, 3762 (1992). See also M. Plischke, J.D. Shore, M. Schroeder, M. Siegert, and D.E. Wolf, *ibid.* **71**, 2509 (1993) and S. Das Sarma and S.V. Ghaisas, *ibid.* **71**, 2510 (1993).
- ⁹ M.R. Wilby, D.D. Vvedensky, and A. Zangwill, *Phys. Rev. B* **46**, 12896 (1992); (errata) *ibid.* **47**, 16068 (1993).
- ¹⁰ J. Krug, M. Plischke, and M. Siegert, *Phys. Rev. Lett.* **70**, 3271 (1993); (errata) *ibid.* **71**, 949 (1993).
- ¹¹ M. Schroeder, M. Siegert, D.E. Wolf, J.D. Shore, and M. Plischke, *Europhys. Lett.* **24**, 563 (1993)..

- ¹² S.F. Edwards and D.R. Wilkinson, Proc. Roy. Soc. London Ser. A **381**, 17 (1982).
- ¹³ W.W. Mullins, J. Appl. Phys. **28**, 333 (1957).
- ¹⁴ L.-H. Tang and T. Natterman, Phys. Rev. Lett. **66**, 2899 (1991).
- ¹⁵ In many cases, it is very difficult (or maybe impossible) to establish an explicit connection between a specific microscopic model and a continuum differential equation. In fact, we know about the only systematic attempt to obtain a continuum equation from the rules of a discrete model [D.D. Vvedensky, A. Zangwill, C. Luse, and M.R. Wilby, Phys. Rev. E **48**, 852 (1993)] but even this method employs several approximations. In this paper, we compare the results from simulations of the WV model with results from various continuum models proposed to describe MBE growth as it is usual in literature but the reader should keep the above caveat in mind.
- ¹⁶ G.H. Gilmer and P. Bennema, J. Appl. Phys. **43**, 1347 (1972); J.D. Weeks and G.H. Gilmer, Adv. Chem. Phys. **40**, 157 (1979).
- ¹⁷ The procedure described in the paper cited in Ref. 15 does not provide the EW term for the WV model (just the ordinary nonlinear equation proposed in Refs. 4,6) [D.D. Vvedensky (private communication)].

FIGURES

FIG. 1. Surface width *vs.* time for the WV model in 1+1 D ($L = 150(\triangle), 300(\times), 600(\square), 800(\circ), 1000(\bullet), 2000(\diamond)$, and $40\,000(\blacksquare)$). Notice that data for larger lattice sizes ($L \geq 800$) were offset to avoid overlapping of data points.

FIG. 2. Surface width *vs.* time for the WV model in 2+1 D ($L = 500(\triangle)$ and $1000(\circ)$). Data for $L = 1000$ were offset to avoid overlapping of data points. The inset shows the last seven data points for $L = 1000$ in semilogarithmic ($\bullet$) and double logarithmic ($\circ$) scales (see text).

FIG. 3. (a) The height–height correlation function $G(r, t)$ in 1+1 D for $L = 40\,000$ and the times $t = 2^1(\circ), 2^4(\bullet), 2^7(\diamond), 2^{10}(\times), 2^{13}(\square), 2^{16}(*), 2^{19}(\triangle), 2^{22}(+)$, and for $L = 2000$ and $t = 2^{27}(\blacksquare)$; (b) The height–height correlation function $G(r, t)$ in 2+1 D for $L = 500$ and the times $t = 2^2(*), 2^4(\square), 2^6(\times), 2^8(\triangle), 2^{10}(\bullet), 2^{12}(\circ), 2^{14}(\diamond)$, and $2^{17}(\blacksquare)$. The insets show the power–law increase of $G(1, t)$.